



Synteen Technical Fabrics, Inc.

SYNTEEN SC41K HIGH STRENGTH POLYESTER GEOTEXTILE FABRICS

SC41K is composed of high molecular weight, high tenacity multifilament polyester yarns that are woven into a stable network placed under tension. Synteen SC Fabrics are inert to biological degradation and are resistant to naturally encountered chemicals, alkalis and acids.

SC41K APPLICATIONS

Reinforced Slopes	Retaining Walls
Road and Embankments Construction	Geotextile Tubes
Soft Soil Subgrade Stabilization	Landfill, Lagoon and Sludge Pond Closures
Geosynthetic Horizontal Drains	

REINFORCEMENT PROPERTIES		TEST METHOD	MARV VALUES	
			Lbs/ft	kN/m
Ultimate Tensile Strength	MD	ASTM D 4595	41,160	600.4
Tensile Strength at 5% Strain	MD	ASTM D 4595	15,229	222.1
Creep Reduced Strength	MD	ASTM D 5262	25,565	372.9
Long Term Design Strength (LTDS)	MD	GRI GT-7	19,696	287.3
Ultraviolet Resistance (500 Hours)		ASTM D 4355	65 %	
PHYSICAL PROPERTIES		UNIT	VALUES	
Roll Dimensions (width x length)		Feet	15' x 300'	
Roll Area		Square Yards	500	

RF Creep - 1.61
 RF Durability - 1.10
 RF Installation Damage - 1.18

SYNTEEN Technical Fabrics, Inc Warranty: Synteen Technical Fabrics warrants our products to be free from defects in material and workmanship when delivered to our customers and that our products meet our published specifications. If a product is found to be defective, and our customer gives notice to Synteen Technical Fabrics before installing the product, Synteen Technical Fabrics will replace the product without charge to our customer or refund the purchase price at Synteen Technical Fabrics election. Replacing the product or obtaining a refund are the buyer's sole remedy for a breach and Synteen Technical Fabrics will not be liable for any consequential damage attributed to a defective product. This warranty is given in lieu of all other warranties, express or implied, including the implied warranty of merchantability or fitness for a particular purpose. There are no warranties which extend beyond the description provided herein.